

# TECHNICAL DATA SHEET

## LEGF138

TAB.1 - Mechanical data

Hardness as cast	n.d.
Hardness hardened	n.d.
Tensile strength	630 MPa
Yield strength	560 MPa
Elongation	55 %

TAB.2 - Physical data

Color	Silver
Colour Coordinates	n.d.
Density	8.56 g/cm <sup>3</sup>
Melting Range	Solidus: 130 °C Liquidus: 140 °C

TAB.3 - Heat treatments

Solution annealing	n.d.
Recrystallization Annealing	n.d.
Hardening	n.d.