

TECHNICAL DATA SHEET

PLAST682HC + Ag0% - 917 ‰

Master alloy for the production of yellow 750 - 875 - 917 ‰ gold jewellery obtained by mechanical working. The elements contained in this product ensure a high surface quality and a high deformation capability thanks the small grain structure, making it suitable for the production of hand and machine made hollow and solid chains, deep drawn items and tube. The use is suggested with the addition of 0 - 40 % of pure silver to the master alloy.

TAB.1 - Mechanical data

Hardness as cast	92 HV
Hardness hardened	n.d.
Tensile strength	325 MPa
Yield strength	157 MPa
Elongation	27 %

TAB.2 - Physical data

Color	Deep yellow
Colour Coordinates	L*: 86.61 a*: 8.66 b*: 24.47
Density	17.42 g/cm ³
Melting Range	Solidus: 928 °C Liquidus: 947 °C

TAB.3 - Heat treatments

Solution annealing	675 °C - 20 min
Recrystallization Annealing	700 °C - 30 min
Hardening	275 °C - 180 min

TAB.4 - Mechanical working parameters

Premelting temperature	1047 °C
Casting Temperature	Min: 997°C Max: 1097 °C
First thickness reduction	Lamination: 50 %Drawing: 25 %
Following thickness reductions	Lamination: 75 %Drawing: 50 %
Pickling after annealing	H2SO4: 20 %Temp: 50 °C - 5 min