

TECHNICAL DATA SHEET

SPARK550M

Brass for the production of jewels and models obtained by investment casting. The elements contained in this product ensure a high deoxidation after casting and a high surface quality, making it suitable for castings with and without stones in place.

TAB.1 - Mechanical data

Hardness as cast	140	HV
Hardness hardened	n.d.	
Tensile strength	450	MPa
Yield strength	220	MPa
Elongation	30	%

TAB.2 - Physical data

Color	Premium white		
Colour Coordinates	L*:	87.80	
	a*:	0.41	
	b*:	4.31	
Density	8	g/cm ³	
Melting Range	Solidus:	843	°C
	Liquidus:	919	°C

TAB.3 - Heat treatments

Solution annealing	675 20	°C min
Recrystallization Annealing	675 20	°C min
Hardening	275	°C
	180	min

TAB.4 - Investment casting parameters

Premelting temperature		1020	°C
Casting Temperature	Min: Max:	900 1050	°C °C
Water investment powder ratio		36-38	%
Flask temperature	Min: Max:	450 700	°C °C
Quenching time without stones in place	Min: Max:	5 20	min min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4: Temp: Time:	20 50 50	% °C min