

TECHNICAL DATA SHEET

SPARK696LRC + Ag13% - 417 ‰

Master alloy for the production of red 375 - 417 - 585 ‰ gold jewellery obtained by investment casting. The elements contained in this product ensure a high deoxidation in casting and a high surface quality, making it suitable for castings with and without stones in place. The use is suggested with the addition of 10 - 20 % of pure silver to the master alloy.

TAB.1 - Mechanical data

Hardness as cast	110	HV
Hardness hardened	n.d.	
Tensile strength	346	MPa
Yield strength	142	MPa
Elongation	46	%

TAB.2 - Physical data

Color	Deep red		
Colour Coordinates	L*:	89.13	
	a*:	7.06	
	b*:	16.66	
Density	11.48	g/cm ³	
Melting Range	Solidus:	848	°C
	Liquidus:	925	°C

TAB.3 - Heat treatments

Solution annealing	636	°C
	20	min
Recrystallization Annealing	636	°C
	20	min
Hardening	n.d.	
	n.d.	

TAB.4 - Investment casting parameters

Premelting temperature		1025	°C
Casting Temperature	Min:	975	°C
	Max:	1075	°C
Water investment powder ratio		36-38	%
Flask temperature	Min:	450	°C
	Max:	700	°C
Quenching time without stones in place	Min:	5	min
	Max:	20	min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4:	20	%
	Temp:	50	°C
	Time:	50	min