

TECHNICAL DATA SHEET

STAR694H + Ag18% - 917 ‰

Universal master alloy for the production of yellow 875 - 917 ‰ gold jewellery obtained by investment casting and mechanical working. The elements contained in this product ensure a high surface quality in investment casting, while in mechanical working a high deformation capability thanks the small grain structure, making it suitable for the production of hand and machine made hollow and solid chains, deep drawn items and tube. The use is suggested with the addition of 10 - 20 % of pure silver to the master alloy.

TAB.1 - Mechanical data

Hardness as cast	95	HV
Hardness hardened	n.d.	
Tensile strength	329	MPa
Yield strength	155	MPa
Elongation	28	%

TAB.2 - Physical data

Color	Deep yellow		
Colour Coordinates	L*:	86.55	
	a*:	8.91	
	b*:	24.01	
Density	17.35	g/cm ³	
Melting Range	Solidus:	942	°C
	Liquidus:	961	°C

TAB.3 - Heat treatments

Solution annealing	675 20	°C min
Recrystallization Annealing	675 20	°C min
Hardening	275 180	°C min

TAB.4 - Investment casting parameters

Premelting temperature		1061	°C
Casting Temperature	Min: Max:	1011 1111	°C °C
Water investment powder ratio		36-38	%
Flask temperature	Min: Max:	450 700	°C °C
Quenching time without stones in place	Min: Max:	5 20	min min
Quenching time with stones in place		15	min in boiling water
Pickling	H2SO4: Temp: Time:	20 50 50	% °C min

TAB.5 - Mechanical working parameters

Premelting temperature		1061	°C
Casting Temperature	Min: Max:	1011 1111	°C °C
First thickness reduction	Lamination: Drawing:	50 25	% %
Following thickness reductions	Lamination: Drawing:	75 50	% %
Pickling after annealing	H2SO4: Temp: Time:	20 50 5	% °C min